

Anti-Static File
STAT—3SF Specifications

Techno Stat Corporation

NON-AMINE ANTI-STATIC(NON-SURFACTANT)、POLYMER ANTI-STATIC BAG

Material Character	Surface Resistivity: Electro - Tech Systems, Inc Model 873 Wide Range Resistance Meter Probe Type: Concentric ring probe Applied voltage: 100V Measurements: 23°C × 50%RH Static Decay Rate: Electro – Tech Systems, Inc Model 406D Static Decay Meter Applied voltage: 5000V (Evaluation by the charge on the positive and negative side) Measurements: 23°C × 50%RH
Properties	Color: Clear Thickness : 0.3mm (300 μ)
Performance	Surface Resistivity(23°C/50%RH) : 8.3×10^9 (Outside) 4.6×10^9 (Inside) Static Decay Rate(23°C/50%RH) : 5Kv→50v 0.02 seconds(+/-side)
<u>These are not guarantee value</u> Technostat Corporation Head office/Factory: 5-381 Shimoatusaki Nasushiobara-shi, Tochigi, Japan TEL: 81+287-60-5311 FAX: 81+287-60-5312 Tokyo Branch: 4F 2-25 Naka-cho Omiya-ku, Saitama-shi, Saitama, Japan TEL: 81+48-650-0007 FAX: 81+48-650-0038	