

## Anti-Static Name Holder

### STAT - 3SN Specifications

**Techno Stat Corporation**

NON-AMINE ANTI-STATIC(NON-SURFACTANT)、 POLYMER ANTI-STATIC BAG

Material Character	<ol style="list-style-type: none"><li>1. Non-Shifted any Surfactant</li><li>2. Surface Resistivity is less than <math>10^{11}</math> /Sq</li><li>3. Using Non-Surfactant Anti-Static Film: STAT-3S (Inside and Outside)</li></ol>
Properties	Color: Clear Thickness : 0.3mm (300 $\mu$ ) (Stat-3S 50 $\mu$ / PP 200 $\mu$ / STAT-3S 50 $\mu$ )=300 $\mu$
Performance	Surface Resistivity(50%RH) : $<10^{11}$ /Sq(Outside) JIS K6911 $<10^{11}$ /Sq (Inside) JIS K6911  Static Decay Rate(50%RH) : 5Kv 50v < 2seconds
<p><u>These are not guarantee value</u></p> <p><b>Technostat Corporation</b> <b>Head office/Factory:</b> 5-381 Shimoatusaki Nasushiobara-shi, Tochigi, Japan TEL: 81+287-60-5311 FAX: 81+287-60-5312 <b>Tokyo Branch:</b> 4F-2-25 Naka-cho Omiya-ku, Saitama-shi, Saitama, Japan TEL: 81+48-650-0007 FAX: 81+48-650-0038</p>	